


Lava™ All-Ceramic System


Preparation for Lava™ Crowns & Bridges

Ideally, the preparation includes a circumferential shoulder or chamfer with a horizontal angle of at least 5°. The vertical preparation angle should be at least 4°. The inside angle of the shoulder preparation must be given a rounded contour. All occlusal and incisal edges should also be rounded.


The marginal edge of the preparation needs to be continuous and clearly visible. A bevel should be avoided. For posterior and anterior teeth, a supragingival margin poses no problems. Due to the tooth-colored framework, very aesthetic results can be achieved.

**Anterior Crown**

- 1.5 - 2.0 mm incisal reduction
- 1.0 - 1.5 mm labial and lingual reduction
- Round the internal line angles
- Chamfer margin

**Posterior Crown**

- 1.5 - 2.0 mm occlusal/incisal reduction
- 1.0 - 1.5 mm axial reduction
- Round the internal line angles
- Chamfer margin

**Special Preparations****Tangential Preparation**

Steep tangential preparations may result in extremely thin tapered margins. In principle, this type of preparation is possible, but caution is advised.

Unacceptable Preparation for Lava™ Crowns & Bridges




Gutter Prep: Margin cannot be detected unambiguously.




90° Shoulder: Margin cannot be detected unambiguously.



Undercuts must be avoided.



Parallel Walls: These are somewhat feasible, but a cement gap cannot be milled in this case. This may affect the fit.



Sharp incisal-occlusal edges must be avoided. The rounding radius should be >0.4 mm.



Divergent stumps in the bridge cannot be milled. Due to the restricted path of insertion, inclination of the two stumps cannot be realized.

3M ESPE

Dental Products

3M Center
Building 275-2SE-03
St. Paul, MN55144-1000

Distributed by

CONTINENTAL
Dental Laboratories
of California

Authorized Milling Center
(800) 443-8048

Preparation for Maryland Bridges

Preparation Depth: Up to 0.7 mm; The preparation needs to be in enamel instead of dentin. The enamel depth of a tooth can vary from 0.4 to 1.0 mm. Wall thickness of zirconia framework: 0.5 mm minimum to ensure sufficient strength.

Veneering: 0.1 mm (Glazing is necessary to prevent abrasion of antagonist); If the preparation depth can not be realized with the minimum wall thickness of 0.6 mm (zirconia + glazing) due to insufficient enamel thickness, the dentist should re-evaluate this indication. If the zirconia is not glazed, the restoration should not have any occlusal contact. We recommend the use of a preparation matrix, before tooth preparation, to be able to check the preparation depth.

For the preparation of retentive elements see figure 1 and 3 (e.g. pinholes, seating groove). A radius of ≥ 0.4 mm is required for the Lava™ milling system.




Figure 1: Rounded angles (Radius ≥ 0.4 mm, no sharp edges), clear margin and horizontal angle $\geq 2^\circ$.




Figure 2: Retentive element: rounded ridge (Radius ≥ 0.4 mm).




Figure 3: Retentive element: rounded pinhole (no sharp edges, radius ≥ 0.4 mm).

Remember: Adhesive & inlay bridges are complex. It's important to follow guidelines to avoid inferior marginal adaptation and lengthy manual fitting efforts after milling.




Figure 4: Not possible: circular preparation of the wings, no preparation in the middle, only one preparation margin can be detected by the system.

3M ESPE
Dental Products
3M Center
Building 275-2SE-03
St. Paul, MN 55144-1000

Distributed by

CONTINENTAL
Dental Laboratories
of California

Authorized Milling Center
(800) 443-8048

Preparation for Inlay Bridges

Preparation Depth: 2-4 mm; It is important to have sufficient space for a connector of 9 mm^2 . The preparation should have a taper of $\geq 2^\circ\text{-}3^\circ$ and have no friction. The margins must be clearly indicated. Full ceramic preparation in general requires rounded angles (no sharp edges, minimum radius ≥ 0.4 mm). Wall thickness of zirconia inlay: ≥ 0.5 mm.

Veneering: Veneering or glazing is necessary to prevent abrasion of antagonist. Maximal length of pontic: 10 mm.




Figure 5: Proximal view inlay prep.




Figure 6: Occlusal view inlay prep.





Figure 7A and 7B: Additional lingual or vestibular wing only with an extension maximally until the tooth equator.



In the case of vestibular and lingual/palatinal wings in addition to the inlay cavity, the wings can be prepared by the Lava™ system maximally until a 90° angle to the inlay preparation (see figure 7A & 7B).